

PRODUCT SPECIFICATION SHEET

BELZONA 5892

FN10106



GENERAL INFORMATION

Product Description:

Cost effective, two component, high temperature coating system applied by Brush or Spray, suitable for continuous immersion in aqueous/hydrocarbon systems up to 203°F/95°C.

Also suitable for dry heat and steaming out up to 410°F/210°C.

Exhibits excellent corrosion resistance at elevated temperatures and is resistant to a wide range of chemicals.

Additionally, it can also be used for creation of irregular load bearing shims via Injection.

Application Areas:

When mixed and applied as detailed in the Belzona Instructions for Use (IFU), the system is ideally suited for application to the following:

- Boiler Feed Water Systems
- Condensate Tanks
- Condensers
- Evaporators
- Heat Exchangers
- Hot Water Vessels
- Pipework
- Separators
- Storage Tanks

APPLICATION INFORMATION

Application Methods

Brush
Heated Airless Spray (single component, plural component, spin spray)
Injection

Application Temperature

Application should ideally occur in the following ambient temperature range: 50°F/10°C to 104°F/40°C

Coverage Rate

The **Belzona 5892** should be applied in 2 coats to achieve a minimum thickness of 16 mil (400 micron).

The theoretical coverage rate at 16 mil (400 micron) is 27 sq.ft. (2.5m²)/litre.

Refer to the Instructions For Use for practical coverage rate guidelines.

Cure Time

Cure times will vary depending on the ambient conditions; consult the Belzona IFU for specific details.

Mixed Properties

Colour: Grey or White
Density: 1.49 g/cm³
Viscosity (BS 5350-B8): 50-65 P (77°F/25°C) & 10-20 P (104°F/40°C)
Gel Time (BS 5350-B5): 150-210 minutes (68°F/20°C)
Sag Resistance (BS 5350-B9): >500 µm / >20 mils
60° Specular Gloss (ASTM D2457): 90 - 100 Gloss Units
VOC content (ASTM D2369 / EPA ref. 24): 0.53% / 7.89 g/L

Mix Ratio (base : solidifier)

3.5 : 1 (pbv) and 5.74 : 1 (pbw)

Overcoat Window

Overcoat times will vary depending on the ambient conditions; consult the Belzona IFU for specific details.

At 68°F/20°C, the maximum overcoat time will typically be 24 hours.

Working Life

The working life will vary according to the temperature. At 68°F/20°C, the usable life of mixed material will typically be 40 minutes, consult the Belzona IFU for specific details.

The above application information serves as introductory guide only. For full application details including the recommended application procedure/technique, refer to the Belzona IFU which is enclosed with each packaged product.

PRODUCT SPECIFICATION SHEET

BELZONA 5892

FN10106



ELONGATION & TENSILE PROPERTIES

When determined in accordance with ASTM D638, typical values will be:

Tensile Strength

3,084 psi / 21.26 MPa (68°F/20°C cure & //68°F/20°C test)
 5,255 psi / 36.23 MPa (212°F/100°C post-cure & 68°F/20°C test)
 5,793 psi / 39.94 MPa (212°F/100°C post-cure & 212°F/100°C test)

Elongation

0.42 % (68°F/20°C cure & 68°F/20°C test)
 0.77 % (212°F/100°C post-cure & 68°F/20°C test)
 4.60 % (212°F/100°C post-cure & 212°F/100°C test)

Young's Modulus

8.34x10⁵ psi / 5,750 MPa (68°F/20°C cure & 68°F/20°C test)
 7.89x10⁵ psi / 5,440 MPa (212°F/100°C post-cure & 68°F/20°C test)
 1.46x10⁵ psi / 1,010 MPa (212°F/100°C post-cure & 212°F/100°C test)

EXPLOSIVE DECOMPRESSION

When tested in accordance with NACE TM0185 using a seawater/crude oil test fluid over-pressured with 1% carbon dioxide/99% methane, the coating exhibits no breakdown after a 21 day immersion period at 158°F/70°C and 70 bar followed by decompression over 15 minutes.

FLEXURAL PROPERTIES

When determined in accordance with ASTM D790, typical values will be:

Flexural Strength

5690 psi / 39.2 MPa (68°F/20°C cure & 68°F/20°C test)
 9180 psi / 63.3 MPa (212°F/100°C post-cure & 68°F/20°C test)
 7980 psi / 55.0 MPa (212°F/100°C post-cure & 212°F/100°C test)

Flexural Modulus

6.86x10⁵ psi / 4730 MPa (68°F/20°C cure & 68°F/20°C test)
 5.47x10⁵ psi / 3770 MPa (212°F/100°C post-cure & 68°F/20°C test)
 4.13x10⁵ psi / 2850 MPa (212°F/100°C post-cure & 212°F/100°C test)

FOOD CONTACT

Direct Food Contact (FDA)

Meets extraction requirements as set out in 21 CFR 175.300 (paragraph c) for a broad range of food types in Conditions of Use B, C, D, E and F (paragraph d).
 Please contact Belzona for more comprehensive data.

HARDNESS

Shore D & Barcol Hardness

The Shore D and Barcol hardness, when determined in accordance with ASTM D2240 and ASTM D2583, will typically be:

	68°F/20°C cure	212°F/100°C post-cure
Shore D	84	86
Barcol 934-1	26	40
Barcol 935	80	86

Koenig Pendulum

When tested to ISO 1522 the Koenig damping time of the coating will typically be :

190 seconds	ambient cure
186 seconds	post cure

PRODUCT SPECIFICATION SHEET

BELZONA 5892

FN10106



HEAT RESISTANCE

Heat Distortion & Glass Transition Temperature (HDT & T_g)

The HDT and T_g when determined in accordance with ASTM D648 and ISO 11357-2 respectively, will typically be:

Cure temperature	HDT	T _g
68°F/20°C	122°F/50°C	129°F/54°C
140°F/60°C	203°F/95°C	205°F/96°C
176°F/80°C	232°F/111°C	243°F/117°C
212°F/100°C	262°F/128°C	262°F/128°C
248°F/120°C	-	291°F/144°C
302°F/150°C	-	315°F/157°C

Atlas Cell Cold Wall Immersion Test

When tested in accordance with NACE TM 0174 procedure A, the coating will exhibit no blistering or rusting (ASTM D714 rating 10; ASTM D610 rating 10) after 6 months immersion in water at 203°F (95°C).

Electrochemical Impedance Spectroscopy (EIS)

The EIS results ($\log_{10}|Z|_{0.1\text{Hz}}$) determined in accordance with ISO 16773 following Atlas cell testing at 203°F/95°C will be typically:

a) Unexposed:	11.1 $\Omega\cdot\text{cm}^2$
b) Liquid Phase:	10.8 $\Omega\cdot\text{cm}^2$
c) Vapor Phase:	10.8 $\Omega\cdot\text{cm}^2$

Immersion Resistance

Suitable for service at temperatures up to 203°F (95°C) but refer to chemical resistance data for chemical contact limitations.

Steam-out Resistance

The coating will exhibit no failure after 96 hours exposure to pressurized steam at 410°F/210°C

Dry Heat Resistance

The indicated degradation temperature in air based on Differential Scanning Calorimetry (DSC) operated in accordance with ISO11357 is typically 446°F (230°C).

For many applications the product is suitable down to -40°F (-40°C).

Resistance to Water Immersion

When tested in accordance with ISO 2812-2, the coating will show no signs of failure after 6 months continuous immersion in artificial seawater at 104°F/40°C.

IMPACT RESISTANCE

Izod Pendulum

Izod impact strength, when determined in accordance with ASTM D256, will typically be:

	Reversed notched Izod Impact Strength	Un-notched Izod Impact Strength
68°F/20°C cure & test	2.0 KJ/m ² 21.4 J/m	2.4 KJ/m ² 30.3 J/m
28 days at 68°F/20°C cure & test	2.4 KJ/m ² 25.7 J/m	2.6 KJ/m ² 33.1 J/m

Falling Weight

The direct falling weight impact resistance when determined in accordance with ASTM D2794 will typically be:

0.19 kg.m / 16.5 in.lbs	(68°F/20°C cure & 68°F/20°C test)
0.35 kg.m / 30.7 in.lbs	(212°F/100°C post-cure & 68°F/20°C test)

POTABLE WATER APPROVAL

NSF/ANSI/CAN 61

Tested and certified by WQA against NSF/ANSI/CAN 61.



Note: **Belzona 5892** has been found to meet the extraction limits of NSF/ANSI/CAN 600. For product use restrictions visit www.wqa.org

WRAS

Listed in the UK Water Fittings Directory under "Materials which have passed full tests of effect on water quality".



THERMAL PROPERTIES

Thermal Conductivity

When tested in accordance with ASTM E1461-13 at a temperature of 100°C (212°F), the thermal conductivity will typically be 0.379 W/m·K.

Thermal cycling

When tested in accordance with NACE TM0304 the coating exhibited no cracking after 252 cycles between +140°F and -22°F (+60°C and -30°C).

Low Temperature Thermal Shock

Coated steel panels will exhibit no blistering, cracking or delamination after multiple cycles of rapid cooling from 212°F (100°C) to -76°F (-60°C).

PRODUCT SPECIFICATION SHEET

BELZONA 5892

FN10106



THICK FILM CRACKING RESISTANCE

When tested in accordance with NACE TM0104 no cracking was experienced when applied at three times recommended thickness and exposed for 12 weeks in sea water at 104°F (40°C).

SHELF LIFE

Separate base and solidifier components shall have a shelf life of 5 years from date of manufacture when stored in their original unopened containers between 41°F (5°C) and 86°F (30°C).

WARRANTY

This product will meet the performance claims stated herein when material is stored and used as instructed in the Belzona Information For Use leaflet. Belzona ensures that all its products are carefully manufactured to ensure the highest quality possible and are tested strictly in accordance with universally recognized standards (ASTM, ANSI, BS, DIN, ISO, etc.). Since Belzona has no control over the use of the product described herein, no warranty for any application can be given.

AVAILABILITY AND COST

Belzona 5892 is available from a network of Belzona Distributors throughout the world for prompt delivery to the application site. For information, consult the Belzona Distributor in your area.

MANUFACTURER / SUPPLIER

Belzona Limited,
Claro Road, Harrogate,
HG1 4DS, UK

HEALTH AND SAFETY

Prior to using this material, please consult the relevant Safety Data Sheets.

TECHNICAL SERVICE

Complete technical assistance is available and includes fully trained Technical Consultants, technical service personnel and fully staffed research, development and quality control laboratories.

The technical data contained herein is based on the results of long term tests carried out in our laboratories and to the best of our knowledge is true and accurate on the date of publication. It is however subject to change without prior notice and the user should contact Belzona to verify the technical data is correct before specifying or ordering. No guarantee of accuracy is given or implied. We assume no responsibility for rates of coverage, performance or injury resulting from use. Liability, if any, is limited to the replacement of products. No other warranty or guarantee of any kind is made by Belzona, express or implied, whether statutory, by operation of law or otherwise, including merchantability or fitness for a particular purpose.

Nothing in the foregoing statement shall exclude or limit any liability of Belzona to the extent such liability cannot by law be excluded or limited.

Copyright © 2025 Belzona International Limited. Belzona® is a registered trademark.

*Belzona products are
manufactured under an
ISO 9001 Registered
Quality Management System*

